

EUROPEAN PATENT OFFICE

Patent Abstracts of Japan

PUBLICATION NUMBER : 10041113
PUBLICATION DATE : 13-02-98


APPLICATION DATE : 25-07-96
APPLICATION NUMBER : 08196412

APPLICANT : MITSUBISHI MATERIALS CORP;

INVENTOR : MORIMOTO KOICHIRO;

INT.CL. : H01F 1/06 B22F 1/00 C22C 33/02
H01F 1/053

TITLE : RARE EARTH MAGNET MATERIAL
POWDER HAVING SUPERIOR
MAGNETIC CHARACTERISTICS AND
MANUFACTURE THEREOF



ABSTRACT : PROBLEM TO BE SOLVED: To provide rare earth magnet material powder of superior magnetic characteristics which has an $R_2(Fe, Co)_{14}B$ type intermetallic compound phase as a main phase.

SOLUTION: A recrystallization aggregate structure has, as a main phase, a structure in which recrystallized grains comprising a component composition, which has a rare earth element containing Y (hereinafter referred to as R), Fe, Co and B as main components, and which contains 0.001-5.0 atomic % of one or more species out of Zr, Si and Hf (hereinafter referred to as M), and an $R_2(Fe, Co)_{14}B$ type intermetallic compound phase which employs a tetragonal structure whose recrystallized grain diameter is 0.05-50 μ m in average, adjoin one another, and contains R-rich phase in partial grain boundary. In R-(Fe, Co)-B-M based magnet material powder which comprises the structure, the recrystallization aggregate structure contains 0.1-1vol% of a $R(Fe, Co, M)_2$ in volume percentage.

COPYRIGHT: (C)1998,JPO